

## Technical data sheet SST 705

SST 705 is a 2 layer seam sealing tape which is available in several widths and thicknesses.

	<i>Method</i>	<i>Membrane</i>	<i>Adhesive</i>
Composition	N/A	Polyurethane	Polyester
Melting Range	Kofler Bench	180 – 185°C	110 °C
Processing Temperature	N/A	N/A	-35 – 80°C
UV-Stability	SAE J 1960	No	No
Hardness	D-2240	90 A	85 A
Tensile Strength	D-412	68,95 N/mm <sup>2</sup>	15,86 N/mm <sup>2</sup>
Appearance	Visual	Transparent	Transparent
Standard Thickness	N/A	0.05 mm	0.15 mm
Ultimate Elongation	D-412	450 %	500 %
Freeze Point	D-1043	-28°C	N/A
Home Washing	N/A	Yes	Yes
Dry Cleaning	N/A	No	No

### Good bonding with:

- Leather
- Non-woven
- Polycotton
- various filtration materials

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for a particular application or the results to be obtained herein. The information is based on laboratory work with small-scale equipment and does not necessarily indicate any end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the product for the applications disclosed. Full –scale testing and end product performance are the responsibility of the end user. Gluetex GmbH shall not be liable for, and the customer assumes all risk and liability for any use or handling beyond Gluetex's direct control.

**The seller makes no warranties, express or implied, including, but not limited to the implied warranties and fitness for a particular purpose.**